



NO. 773-A

MasterFormat:
07 92 13
32 13 73



NOVEMBER 2015
(Supersedes November 2013)

POURTHANE® SL Self-Leveling Joint Sealant

DESCRIPTION

POURTHANE SL is an elastic, one-component, self-leveling, premium-grade polyurethane sealant specifically developed to be used as a multi-purpose horizontal joint sealant in applications where a high chemical resistance to fuels, oils, and hydrocarbons is required. The product is a moisture cure sealant with excellent adhesive properties and resistance to aging and weathering.

USES

POURTHANE SL is used to seal horizontal expansion joints in concrete and cementitious slabs, such as sidewalks, balconies, pavement, terraces, warehouses, factories, civil structures, plazas, runways, and pitch pans.

FEATURES/BENEFITS

- One-component, no mixing.
- Self-leveling.
- Non-bubbling formula.
- Can be applied to green concrete.
- Movement capacity of +/-25%.
- Accelerated curing.
- Jet fuel resistant.
- Permanently elastic.
- High durability.
- Resists aging and weathering.
- Excellent adhesion.
- Convenient, easy-to-use packaging.
- Low VOC content.

PACKAGING

29 Oz. (825 mL) Cartridges
5 Gal. (18.93 L) Pails
55 Gal. (208.20 L) Drums

AVAILABLE COLORS

Limestone, Stone Gray, Tan

COVERAGE

This chart shows the approximate number of lineal feet that can be sealed per gallon. One gallon is approximately four cartridges.

Joint Depth	Joint Width						
	1/4" (6.4 mm)	3/8" (9.5 mm)	1/2" (12.7 mm)	5/8" (15.9 mm)	3/4" (19.1 mm)	7/8" (22.2 mm)	1" (25.4 mm)
1/4" (6.4 mm)	308	205	154	122			
3/8" (9.5 mm)				82	68	58	51
1/2" (12.7 mm)					51	44	38

When estimating, figure 5 cartridges/gal. (2 cartridges/1.5 L).

Cubic inches/gal. – 231 (1000 cm³)

Cubic inches/cartridge – 21 (344.13 cm³)

For triangular cross-section joints:

1/4" (6.35 mm) each side – 616 linear ft./gal. (49.6 m/L)

1/2" (12.7 mm) each side – 154 linear ft./gal. (12.4 m/L)

3/4" (19.1 mm) each side – 68 linear ft./gal. (5.5 m/L)

SHELF LIFE

When stored indoors and in original, unopened containers at temperatures between 41 - 77° F (5 - 25° C), shelf life is one year from date of manufacture, except for pails and drums, which have a shelf life of six months.

SPECIFICATIONS

- ASTM C 920-11, Type S, Grade P, Class 25, Use T₁, T₂, NT, M, O, G.
- Conforms to BS 5212 for determination of resistance to heat, aging, and fuel immersion.
- Can/CGSB 19.13-M87, Classification C-1-40-B-N and C-1-25-B-N, No. 81028
- Federal Specification TTS-00230C, Type 1, Class A
- Approval/Standards Conform to ISO 11600 F 25 HM
- USDA compliant for use in areas that handle meat and poultry

CONTINUED ON REVERSE SIDE...

W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976

www.wrmeadows.com

HAMPSHIRE, IL /CARTERSVILLE, GA /YORK, PA
FORT WORTH, TX /BENICIA, CA /POMONA, CA
GOODYEAR, AZ / MILTON, ON /ST. ALBERT, AB

TECHNICAL DATA

Appearance	Pasty
Viscosity @ 74° F (23° C)	Brookfield RVT / spindle 6 / 5 rpm : ca. 15,000 mPa.s
Density @ 73° F (23° C) and 50% RH	1.48 ± 0.02 g/cc
Application Temperature	40 - 100° F (4.4 – 37.8° C)
Skin Formation Time @ 74° F (23° C) and 50% RH	60/120 Min.
Shore A Hardness (ASTM D 2240) 21 Day	35 +/- 5
Temperature Resistance	-40 - 176° F (-40 - 80° C)
Resistance to Dilute Acids and Bases	Average
UV Resistance	Good
Water and Salt Spray Resistance	Excellent
Compatibility w/Paints	Water-Based: Yes Solvent-Based: Test beforehand
Modulus @ Break ASTM D412	>0.6 MPA
Elongation @ Break ASTM D412	>800%
VOC Content	27 g/L

APPLICATION

Surface Preparation ... Clean all surfaces. Joint walls must be sound, clean, dry, frost-free, and free of all oil and grease. Curing compound residues and any other foreign matter must be thoroughly removed. Install bond breaker tape or KOOL-ROD™ from W. R. MEADOWS to prevent bond at base of joint. When applying to green concrete, wait 24 hours after forms have been removed. Concrete can be damp during application, but do not apply when standing water is in or near joints.

**LIMITED WARRANTY**

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

Priming ... Priming is not usually necessary. Substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure. If priming is required, use P/G PRIMER from W. R. MEADOWS.

Application Method ... Condition material to 65° - 75° F (18.3° - 23.9° C) before using. Sealant should be installed when joint is at mid-range of anticipated movement. Gun sealant into joint opening in one direction and allow sealant to flow and level out as necessary. Tool as required; minimum tooling is necessary. Joint dimensions should allow for ¼" (6.35 mm) minimum and ½" (12.7 mm) maximum thickness for sealant. Proper design is 2:1 width-to-depth ratio. Always use bond breaker tape or KOOL-ROD™ from W. R. MEADOWS for support on horizontal joints.

Cleanup ... Application tools can be cleaned with toluene or xylene before curing. Afterwards, mechanical cleaning will be required.

PRECAUTIONS

Allow one-week cure at standard conditions when used in total water immersion applications. Maximum exposure level of chlorine is 5 ppm. Do not cure in presence of curing silicone sealants. Avoid contact with alcohol and other solvent cleaners during cure. Maximum depth of POURTHANE SL should be ½" (12.7 mm). Do not use caulks, sand, or incompressibles as a bottom in a joint. Do not install when rain is expected before the product develops a substantial skin. Storing at elevated temperatures will reduce shelf life.

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 4.1: Low Emitting Materials: Adhesives & Sealants
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.